Preparation and Characterization of Silver Oxide Nanoparticles (AGNPS) and Evaluation the Ratios of Oxides

¹Firas H. Abdulrazzak, ²Ahmed M. Abbas, ¹Mostefe Khalid Mohammed, ²Israa Mohammed Radhi,
¹Ahmed E. Abdullatif, ²Hamsa M. Yaseen, ³Duah Ayad Yas and ⁴Ayad F. Alkaim

¹Department of Chemistry, College of Education for Pure Science, University of Diyala, Baqubah, Iraq

²Department of Chemistry, College of Education for Pure Science, University of Baghdad,
Baghdad, Iraq

³Technical Institute, Baquba, Iraq

⁴Department of Chemistry, College of Science for Women, University of Babylon, Hilla, Iraq
firas_habeb2000@yahoo.com

Abstract: Silver nanoparticles (AGNP) were prepared as a mixture of Ag₂O, Ag₂O and Ag from silver nitrate and hydrogen peroxide at room temperature in dark. The process of synthesis includes changing the sequence of addition for AgNO₃ and H₂O₂ in addition to change the concentration of H₂O₂. The structural morphology and optical properties of silver nanoparticles (AGNPS) were characterized by X-Ray Diffraction (XRD), Atomic Force Microscopy (AFM), UV-visible absorbance and Fourier-Transform Infrared Spectroscopy (FTIR). The results showed that the change in routes of addition for materials causing produces the change in the ratios of Ag species. The highest value for Ag nanoparticles was shown for Ag₂ when produces 31.25% while Ag₃ consist 71.10% of AgO. The antibacterial activity for the synthesized AGNPS were shown variances when tested with bacterial *Acinetobacter baumannii* which shows maximum activities with AG3.

Key words: AGNP, H₂O₂, *Acinetobacter baumannii*, XRD, AFM, AgO

INTRODUCTION

Nanoparticles are mono, di or tri dimensions with 1-100 nm in the size (Hasan, 2015) when emerging with science forming nanoscience. The pattern which is owned by nanoparticles can be related to rare physical and chemical properties as compared to their bulk materials. Mostly, the specific properties with electronic structures cause large reactive surface area and quantum size (Hodes, 2007). The amazing properties encourage to use nanoparticles in huge fields such as electronics, photochemical, biomedicine, polishing and coatings (Saez and Mason, 2009). Jawaad *et al.* (2014) reported that AGNPS is commonly used to kill microbe by abilities to interact with different conditions which variance with the morphology of nanoparticles such spherical, cubic and triangular prism. These types can be prepared use organic, inorganic or hybrid of organic and inorganic materials by thermal or vapor decomposition (Henglein, 1993; Sopousek *et al.*, 2012), microemulsions or chemical reduction methods (Merza *et al.*, 2012). The large surface area to volume ratio for metallic enhances bactericidal properties when showing resistance against the growing microbial and success to the development of resistant

strains (Gong *et al.*, 2007). Mostly, the silver nanoparticles were synthesis in aqueous solution by reduction of Ag⁺ to forming colloidal of Ag⁰ with nanometers in diameter. The colloidal of Ag⁰ which followed by produce agglomeration of Ag clusters. The first indicator that proves the forming nanoparticles represent by an intense band in the 380-400 nm for yellow color in the absorption spectrum. Hussain *et al.* (2011) used aniline as reductant and oxidant, respectively, to the growth of silver nanocrystals from silver nitrate. The interparticle interaction of aniline with Ag-nanocrystals on the surface and electrostatic interactions due exist lone-pairs electrons of amine groups with positive surface of Ag-nanoparticles enhance forming nano size. Silva *et al.* (2013) used H₂O₂ between 0.4 and 0.6% (V/V) which represent ideal value to produce AGNPS. Dimitrijevic *et al.* (2013) synthesized spherical nanoparticles in large quantity by using a modified method of hydrolytic decomposition of silver complexes with amino types in ethanol aqueous solution. Awwad and Salem (2012) used green chemistry to synthesized Ag nanoparticles from deferent natural sources such plant which produces inorganic nanoparticles by photo or electro chemical reduction and

heat evaporation methods. Jyoti *et al.* (2016) used aqueous leaves extract of *Urtica dioica* for synthesis of AGNPS. Many efforts were done to synthesis Ag as nanoparticles AGNPS which appears mostly with different ratios of oxidation for Ag. In this research, Ag nanoparticles were prepared as a mixture of Ag^0 , Ag^{+1} and Ag^{+2} by using three ways the first two ways include the same conditions with changing the sequence of additions. The third ways were the same conditions of the first only the change was the double in the concentration of H_2O_2 . Simple and easy reaction was done to reach for best ratios of AGNPS. All the samples were characterized by X-ray diffraction, Atomic Force Microscopy (AFM), optical property and Fourier-Transform Infrared Spectroscopy (FTIR).

MATERIALS AND METHODS

Experimental: Silver nitrate (AgNO_3) salt was supplied by Sigma-Aldrich. The hydrogen peroxide H_2O_2 was purchase from Barcelona, Spain in 30% weight, all materials were used without any purification. Three samples were prepared AG3, AG2 and AG3 in dark. The first sample AG3 was prepared by dissolved 0.5 g of AgNO_3 in 10 mL of distilled water which drop wise to 20 mL hydrogen peroxide 15% (V/V%) at 10°C by using separation funnel as shown in Fig. 1a. After complete additions AgNO_3 solution, the mixture kept in dark for 5 h at room temperature. The precipitation was removed from the solution and drying at 7°C at N_2 gas atmosphere for 10 h. The second sample AG2 was prepared by dropped H_2O_2 onto AgNO_3 solution which is opposite the ways of forming AG3. The third sample AG3 was prepared as AG3 with double concentration of H_2O_2 to 30%.

Characterizations: The elemental composition of as prepared samples was determined by X-Ray Diffraction (XRD) patterns with a (Riga Rotaflex-RU-200B) using $\text{Cu K}\alpha$ radiation (wavelength 0.15405 nm) at room temperature. The 2θ angular regions between 10 and 80° were explored at a scan rate of $5^\circ/\text{min}$. For all the XRD analysis, the resolution in the 2θ scans was kept at 0.02° . The optical properties of the samples were examined by using a UV-Visible spectrophotometer at the normal incidence of light in the wavelength range of 200-1100 nm. Fourier Transfer Infrared (FT-IR) spectra were measured on a Shimadzu IRAffinity-1 FTIR spectrophotometer with a resolution of 4 cm^{-1} . The spectrum was scanned from ($600\text{--}4000\text{ cm}^{-1}$). Figure 2, refer to X-Ray Diffraction (XRD) pattern of three samples which include four types of AGNP such Ag, AgO and Ag_2O . Mostly the common crystalline planes having cubic orientations (Hofmeister *et al.*, 2005). The three phases of silver which forming are two oxides Ag_2O and AgO with Ag nanoparticles. The three samples AG1-AG3 show the variant in the ratios of three materials this could be attributed to the conditions of precipitations (Nwanya *et al.*, 2013). The compare between AgNO_3 and the three samples can be seen real change in crystallography. The AG3 shows many noises, mostly refer to unconverted AgNO_3 for AGNP and while AG2 and AG3 Distinguished by new structures with new crystallography.

The same results can be seen in Fig. 3 of AFM images for three colloid samples AG1-AG3 when exhibiting different size distributions. The image for AG3 shows many irregular structures with many agglomerates when reaching to 120 nm as shown in Table 1. The reason

Fig. 1: Schematic diagram for synthesis: a) AG1, AG3 and b)Ag

Fig. 2: The XRD pattern of pristine AgNO_3 and synthesized: a) AG1; b) AG2 and c) AG3

Fig. 3: Three dimensions AFM surface images of three synthesized samples: a) AG1; b) AG2 and c) AG3

behind large particle size can be related to addition AgNO_3 for peroxide medium with low ratios H_2O_2 which cause many aggregations prevent AgNO_3 to react with H_2O_2 . The second sample AG2 shows more crystallinity with more regular structure as compare with AgNO_3 and AG3. The behavior of AG2 refers to slowly precipitation for AgNO_3 with drop wise H_2O_2 causing growth different ratios of Ag^0 , Ag^+ and Ag^{+2} . According to UV-Vis spectra (Fig. 2), the AGNP formed present distinct size, since, the position of the main band is related to the area of the formed particles.

AFM image for the three samples was reported in Fig. 3 with a statistical calculation of AFM images were

Table 1: Relative intensity and percentage of Ag types nanoparticles in three samples

Samples	Relative intensity (au)				Percent the type of Ag (%)			
	Ag^+	AgO^*	Ag_2O	$\text{AgO}^\oplus$	% Ag^+	% AgO^*	% Ag_2O^x	% $\text{AgO}^\oplus$
Ag3	2.5	2.8	1.3	4.6	22.32	25.00	11.60	41.07
Ag2	4.0	4.0	2.0	2.8	31.25	31.25	15.62	21.87
Ag3	1.5	0.4	0.1	4.9	21.73	05.79	01.44	71.10

performed using specially designed image processing software in Fig. 4 which listed in Table 1. From the AFM images, we can see many big clusters of nanoparticles appears as aggregates forming during the deposition for AG1 and AG2 while AG3 shows more ravens with less

Fig. 4: Schematic digrame for the percent of diameter for three samples: a) AG1; b) AG2 and c) AG3

Fig. 5: Normalized UV-Vis spectra for three samples AG1, AG2 and AG3

Table 2: The value of average and mode diameters for the nanoparticles in the samples

Samples	Average diameter (nm)	Mode diameter (nm)
Ag3	90.21	120
Ag2	83.95	105
Ag3	57.90	70

value in size of clusters. The results were listed in Table 2 which shows variants in an average diameter in three samples which refer to regular precipitation in sample 3.

The optical property of synthesized silver nanoparticles between 300 and 1100 nm are plotted in Fig. 5. Sample AG2 shows one absorption peak ranging between 350-950 nm refer to high ratios of Ag nanoparticles (Hussain *et al.*, 2011) as compared with AG3 and AG3 samples which are sensitive to synthesis condition.

FTIR analysis in Fig. 6 was performed at room temperature in the range of 600-4000 cm^{-1} . The peak at 1550 and 1506 cm^{-1} was concluded to be Nitrate from AgNO_3 which is starting metal precursor (Muzamil *et al.*, 2014). This peak was reduced for the samples after treatment with H_2O_2 . Hydroxyl group shows a broad band at 3351 cm^{-1} due to bounded stretching and a weak peak at 1637 cm^{-1} for bending vibrations due to hydrogen peroxide which variant with conditions of oxidation AgNO_3 (Mohammadi and Ranjbar, 2017). Mostly, the band appeared at 742 cm^{-1} was assigned to the deformation vibration of AgO (Kumar and Rani, 2013) which disappear with AgNO_3 while with AG1-AG3 show clear. The second beaks Singho *et al.* (2012) refer to AgO stretching at 1635 cm^{-1} when more pronounced in AG2 and AG3 and did not appear in Ag3 and AgNO_3 .

Fig. 6: Continue

Fig. 6: FTIR spectra of: a) AgNO_3 ; b) AG1; c) AG2 and d) AG3 from 4000-600 cm^{-1} wavelength

The XRD pattern in Fig. 2, of the three samples at different ways of addition H_2O_2 shows crystalline nature with cubic orientations (Hofmeister *et al.*, 2005). Ag_2O and AgO are the dominant oxides present with Ag^+ nanoparticles at lower deposition time. It is seen that as the strategy of addition H_2O_2 change the ratios of nanoparticles AgO , Ag_2O and Ag . This could be related to the reaction of Ag^+ with different free radicals species and anions in the solution as shown in suppose equations:

The first reactive species produce from H_2O_2 was $\text{HO}_2^\cdot$ due to unstable and easily produces strong oxidizing agent which represents by $\text{HO}^\cdot$. As shown in the mechanism three species: $\text{O}^\cdot$, $\text{HO}^\cdot$ and $\text{O}_2^\cdot$ that responsible to produces AGNP with variance in the state. The ratios and types of AGNP depend on the concentration $\text{H}_2\text{O}_2/\text{AgNO}_3$ and the nature of species that react with dissolved Ag^+ particles. It is seen that when AgNO_3 was dropped into H_2O_2 , the AgO becomes the dominating AGNP while opposite addition enhances forming Ag more than another species of AGNP. This may

be attributed to the reaction of Ag^+ or Ag^{+2} with OH^- as free radicals or anions and the reaction of forming Ag with OH^- at peroxide media. This behavior became more pronounced when the concentration of hydrogen peroxide double which causes high ratios of AgO and Ag_2O as compare with Ag .

RESULTS AND DISCUSSION

Antibacterial activity: The antibacterial activity of silver compounds were tested by bacterial *Acinetobacter baumannii* to assess the susceptibility activity with using disc diffusion method. The concentration of pristine AgNO_3 and synthesized AGNPs were (1 mg/mL) in aqueous solution which loaded 100 μL at 37°C for 24 h as shown in Fig. 7a. The activities were evaluated by measuring the diameter of inhibition zones in micro meter which represented in schemes in Fig. 7b.

The antimicrobial efficacy of silver compound Ag1 and AG2 were more than AG3 and pristine AgNO_3 . The activity can be related to the surface area (Jyoti *et al.*, 2016; Guzman *et al.*, 2008) when increase the active site that attach to the surface of the cell membrane causing disturb the permeability. The binding of the particles to the bacteria depends on the surface area with active sites which is available for interaction, thus, small particles available for interaction with give more bactericidal effect than the large particle.

Fig. 7: a) *Acinetobacter Baumannii* zone of inhibition around silver nanoparticle compounds (AgNO_3 , AG1, AG2, AG3) impregnated disk and b) schemes of activity for the synthesized materials

CONCLUSION

The Ag nanoparticles have been prepared by treatment AgNO_3 with H_2O_2 which causing forming AGNP as a mixture of pristine Ag and Ag oxide. Deposition of silver was carried out with different ratios of species due to change the strategy of additions and concentration of H_2O_2 . XRD analysis showed the converted in crystallography of AgNO_3 to the new structure which mostly consisted of AGNP with three structures AgO , Ag_2O and Ag. AFM analysis showed that the routes of adding hydrogen peroxide to silver nitrate causing variant in the structure of crystals. The conditions of preparations effect directly with the particles size and active site which causing variance in activities with *Acinetobacter baumannii*.

REFERENCES

- Awwad, A.M. and N.M. Salem, 2012. Green synthesis of silver nanoparticles by mulberry leaves extract. *Nanosci. Nanotechnol.*, 2: 125-128.
- Dimitrijevic, R., O. Cvetkovic, Z. Miodragovic, M. Simic and D. Manojlovic *et al.*, 2013. SEM/EDX and XRD characterization of silver nanocrystalline thin film prepared from organometallic solution precursor. *J. Min. Metall. B. Metall.*, 49: 91-95.
- Gong, P., H. Li, X. He, K. Wang and J. Hu *et al.*, 2007. Preparation and antibacterial activity of Fe_3O_4 Ag nanoparticles. *Nanotechnology*, 18: 604-611.
- Guzman, M.G., J. Dille and S. Godet, 2008. Synthesis of silver nanoparticles by chemical reduction method and their antibacterial activity. *Intl. Scholarly Sci. Res. Innovation*, 2: 91-98.
- Hasan, S., 2015. A review on nanoparticles: Their synthesis and types. *Res. J. Recent Sci.*, 4: 9-11.
- Henglein, A., 1993. Physicochemical properties of small metal particles in solution: Microelectrode reactions, chemisorption, composite metal particles and the atom-to-metal transition. *J. Phys. Chem.*, 97: 5457-5471.
- Hodes, G., 2007. When small is different: Some recent advances in concepts and applications of nanoscale phenomena. *Adv. Mater.*, 19: 639-655.
- Hofmeister, H., G.L. Tan and M. Dubiel, 2005. Shape and internal structure of silver nanoparticles embedded in glass. *J. Mater. Res.*, 20: 1551-1562.
- Hussain, J.I., S. Kumar, A.A. Hashmi and Z. Khan, 2011. Silver nanoparticles: Preparation, characterization and kinetics. *Adv. Mat. Lett.*, 2: 188-194.
- Jawaad, R.S., K.F. Sultan and A.H. Al-Hamdani, 2014. Synthesis of silver nanoparticles. *ARNP. J. Eng. Appl. Sci.*, 9: 586-592.
- Jyoti, K., M. Baunthiyal and A. Singh, 2016. Characterization of silver nanoparticles synthesized using *Urtica dioica* Linn. leaves and their synergistic effects with antibiotics. *J. Radiat. Res. Applied Sci.*, 9: 217-227.
- Kumar, H. and R. Rani, 2013. Structural characterization of silver nanoparticles synthesized by micro emulsion route. *Intl. J. Eng. Innovative Technol.*, 3: 344-348.
- Merza, K.S., H.D. Al-Attabi, Z.M. Abbas and H.A. Yusr, 2012. Comparative study on methods for preparation of gold nanoparticles. *Green Sustainable Chem.*, 2: 26-28.
- Mohammadi, K. and M. Ranjbar, 2017. Preparation of AgO_2/GrO nanocomposites by hydrothermal method and investigation of photoluminescence properties. *J. Mater. Sci. Electron.*, 28: 3185-3190.

- Muzamil, M., N. Khalid, M.D. Aziz and S.A. Abbas, 2014. Synthesis of silver nanoparticles by silver salt reduction and its characterization. IOP. Conf. Ser. Mater. Sci. Eng., 60: 012034-012041.
- Nwanya, A.C., P.E. Ugwuoke, B.A. Ezekoye, R.U. Osuji and F.I. Ezema, 2013. Structural and optical properties of chemical bath deposited silver oxide thin films: Role of deposition time. Adv. Mater. Sci. Eng., 2013: 1-8.
- Saez, V. and T.J. Mason, 2009. Sonoelectrochemical synthesis of nanoparticles. Molecules, 14: 4284-4299.
- Silva, J.N., J. Saade, P.M. Farias and E.H.L. Falcao, 2013. Colloidal synthesis of silver nanoprisms in aqueous medium: influence of chemical compounds in UV/Vis absorption spectra. Adv. Nanoparticles, 2: 217-222.
- Singho, N.D., N.A.C. Lah, M.R. Johan and R. Ahmad, 2012. FTIR studies on silver-poly (methylmethacrylate) nanocomposites via in-situ polymerization technique. Intl. J. Electrochem. Sci., 7: 5596-5603.
- Sopousek, J., J. Bursik, J. Zalesak and Z. Pesina, 2012. Silver nanoparticles sintering at low temperature on a copper substrate: In situ characterization under inert atmosphere and air. J. Min. Metall., Sect. B. Metall., 48: 63-71.